



CEWELD MA SS 2343 Tig

TYPE	Solid welding wire for hardfacing and rebuilding hotworking tools..					
ANWENDUNGEN	Rebuilding and hardfacing parts that are subject to abrasion combined with higher temperatures.					
EIGENSCHAFTEN	Abrasion combined with higher temperatures.					
KLASSIFIKATION	EN ISO W.Nr.	14700: S Fe3 1.2343				
GEEIGNET FÜR	Hotworking tools, high speed tool steels, HSS, aluminium press molts, dies, stamping tools, cutting tools, shear blades, cutters, knives, scissors.					
ZULASSUNGEN						
SCHWEISSPOSITIONEN	      					
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	C 0.4	Mn 0.4	Cr 5	Mo 1.1	V 0.5	Fe Rem. Si 1
MECHANISCHE GÜTEWERTE	Heat Treatment As Welded		R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness 55 HRc
RÜCKTROCKNUNG	Not required					
GAS ACC. EN ISO 14175	I1					



CEWELD MA SS 2343 Tig

MA SS 2343 TIG 1,0 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720682051825

MA SS 2343 TIG 1,6 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663401816

MA SS 2343 TIG 2,0 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663401854

MA SS 2343 TIG 2,4 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663401793

MA SS 2343 TIG 3,0 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663401809