



CEWELD 16.8.2 Tig

TYPE	A specially designed hybrid alloy between 308H and 316H for high temperature applications.								
ANWENDUNGEN	Used mainly in power generation and chemical process industries on applications such as, steam turbines, catalytic crackers, transfer piping and furnace accessories.								
EIGENSCHAFTEN	A specially designed composition where Molybdenum % is reduced to form a hybrid alloy between 308H and 316H, operates in temperatures up to 800 °C. CEWELD® 16.8.2 Tig gives a very high resistance to thermal embrittlement. Creep ductility is enhanced at temperatures above 650 °C.								
KLASSIFIKATION	AWS	A 5.9: ER16-8-2							
	EN ISO	14343-A: W 16 8 2							
	F-nr	4							
	FM	5							
GEEIGNET FÜR	1.4948, 1.4941, 1.4961, 1.4919, X6CrNi18-10, X8CrNiTi18-10, X8CrNiNb16-13, X6CrNiMoB17-12-2, 304H, 321H , 347H, 316H, UNS 30409, S32109,S34709, S31609, 304S51, 321S51, 347S51, 316S51, 316S53								
ZULASSUNGEN	CE								
SCHWEISSPOSITIONEN	     								
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	C	Si	Mn	P	S	Cr	Ni	Mo	Cu
	0.05	0.4	1.3	0.01	0.003	15.3	8.4	1.2	0.02
MECHANISCHE GÜTEWERTE	Heat Treatment	RP0,2 (MPa)	Rm (MPa)	A5 (%)	Impact Energy (J) ISO-V			Hardness	
					-196°C				
	As Welded	420	850	>35	90			HRc	
RÜCKTROCKNUNG	Not required								
GAS ACC. EN ISO 14175	I1, I3								



CEWELD 16.8.2 Tig

16.8.2 TIG 2,4 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663413253