



CEWELD AA DUR 21

TYPE	Cobalt based fluxcored wire for cladding against metal wear, thermal schock and erosion. (Stellite 21)		
APPLICATIONS	Solving wear problems against chemicals, erosion, corosion, high temperatures, abrasion and combinations of those.Cladding seats and valves in chemical industry, hot sharing blades, extrusion parts, coke hammers, turbine injectors, gas and steam turbine parts.		
PROPERTIES	Excellent gliding properties against metal to metal wear due to low friction, Excellent against erosion and corrosion at high working temperatures upto 900°C. Crack free hard facing deposit against severe shock and impact.		
CLASSIFICATION	AWS EN ISO DIN F-nr	A 5.21: ERCCoCr-E 14700: T Co1 8555: MSG 20-GF-350-CTZ 73	
SUITABLE FOR	CoCr-E Co1 Celist 721		

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	Cr	Ni	Mo	Fe	Co
0.27	1.25	1	28	3	5	3.5	Rem.

MECHANICAL PROPERTIES

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				30 HRc

REDRYING 140°C / 24 hr

GAS ACC. EN ISO 14175 M13



CEWELD AA DUR 21

AA DUR 21 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663402479

AA DUR 21 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663402486