

CEWELD AlSi 12

TYPE Aluminium silicon alloy for welding cast aluminum parts, also suitable as brazing alloy with suitable flux.

APPLICATIONS Aluminium alloy for welding and brazing. This material is generally used for brazing aluminium sheets, for extrusions and castings. (After anodizing the welding will be of a different color)

PROPERTIES AlSi12 was originally developed as a brazing alloy to take advantage of its low melting point and narrow freezing range. In addition, it has a higher silicon content than AlSi5, which provides increased fluidity and reduced shrinkage. Hot cracking is significantly reduced when using AlSi12 as a filler alloy. The alloy may be used in applications at sustained elevated temperatures. Non-heat treatable. Thicker sections should be preheated (150°C) prior to welding.

CLASSIFICATION

AWS	A 5.10: ER4047A
EN ISO	18273: S Al 4047A (AlSi12(A))
W.Nr.	3.2585
F-nr	23

SUITABLE FOR Cast aluminium up to 12% Si:
G-AlSi10Mg, G-AlSi11, G-AlSi12 (Cu), G-AlSi7Mg, G-AlSi6Cu4, G-AlSi9Mg, G-AlSi9Cu3, 4145, 3.2581, 3.2583, 3.2381, 3.2383, 3.2373, 3.2163, 3.2371, 3.2151, B 413.0, 361.0, 359.0, 356.0, 319.0,

APPROVALS CE

WELDING POSITIONS




TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Si	Mn	Ti	Fe	Cu	Zn	Al
	12	0.1	0.1	0.3	0.1	0.1	Rem.

MECHANICAL PROPERTIES	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A5 (%)	Hardness
	As Welded	95	190	6	HRc

REDRYING Not required

GAS ACC. EN ISO 14175 I1, I3



CEWELD ALSi 12

ALSI 12 0,8MM

Packaging	KG/unit	EanCode
D-100	0,5	8720663407719
D-200	2	8720663407726
D-300	7	8720663407764

ALSI 12 1,0MM

Packaging	KG/unit	EanCode
BS-300	7	8720663407771
D-100	0,5	8720663407733
D-200	2	8720663407740

ALSI 12 1,2MM

Packaging	KG/unit	EanCode
D-200	2	8720663407757
D-300	7	8720663407788

ALSI 12 1,6MM

Packaging	KG/unit	EanCode
D-300	7	8720663407795

ALSI 12 2,4MM

Packaging	KG/unit	EanCode
D-300	7	8720663407801