



CEWELD Al 99,0

TYPE 99,0% pure aluminum filler metal for Mig welding

APPLICATIONS Aluminum wire for welding mostly pure aluminum (maximum 0,95% of alloyed elements). Applications in chemistry, electronics, construction and food industries.

PROPRIÉTÉS This 99,0% pure aluminum filler metal offers excellent weldability and is the strongest in the 1000 series of the pure aluminium grades. Heavy parts and thicker plates should be preheated (150°C), prior to welding. At the same time, it keeps the benefits of being relatively lightly alloyed (compared to other series), such as high electrical conductivity, thermal conductivity, corrosion resistance, and workability. It can be strengthened by cold working, but not by heat treatment.

CLASSIFICATION

AWS	A 5.10: ER1100
EN ISO	18273: S Al 1100 (Al99,0Cu)
F-nr	21

CONVIENT POUR Al99,0 Al.99,5 Al.99,7 E-Al., 99,5, 3.0205, 3.0255, 3.0275, 3.0257, EN AW 1200, EN AW 1050A, EN AW 1070A, EN AW 1350, 1060, 1070, 1080, and 3003.

AGRÉMENTS CE

POSITIONS DE SOUDAGE

ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	Mn	Cu	Al	Si+Fe
	0.03	0.1	99.4	0.5

PROPRIÉTÉS MÉCANIQUES	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
	As Welded	52	93	30	HRc

ETUVAGE Not required

GAS ACC. EN ISO 14175 I1, I3