



CEWELD AA B CrMo1

TYPE	Medium alloyed flux-cored wire for CO2 and M 21 with basic slag.						
APPLICATIONS	Steam boiler, pressure vessels, apparatus construction, mechanical engineering, pipe work, steam turbine construction, foundries.						
PROPRIÉTÉS	Absolutely crack resistant weld metal conditioned by the high-basic slag in combination with very low hydrogen content. Suitable for the economic processing on high-temperature resistant CrMo-steels up to 550 °C. X-ray-proof seams with negligible formation of spatter.						
CLASSIFICATION	AWS	A 5.29: E80T5-B2M H4, A 5.36: E80T5-M21PY-B2-H4					
	EN ISO	17634-A: T CrMo1 B M21 3 H5					
	F-nr	6					
	FM	4					
CONVIENT POUR	Typ 1Cr0,5Mo, ISO 15608: ~5,1 1.7335, 1.7262, 1.7728, 1.7218, 1.7225, 1.7258, 1.7354, 1.7357, 1.7205, 1.7218, 1.7225, 1.7228, 1.7254, 1.7262, 1.7335, 1.7337, 1.7350, 1.7354, 1.7357, 13CrMoV42, 13CrMo4-4, 13CrMo4-5, 15CrMo3, 15CrMo5, 13CrMoV42, 15Cr3, 16MnCr5, 20MnCr5, 15CrMo5, 24CrMo5, 25CrMo4, GS-22CrMo5, GS-22CrMo54, GS 17CrMo5-5, 16CrMoV4, 42CrMo4, 42CrMo4V, 41CrMo4V ASTM A 182 Gr. F12; A 193 Gr. B7; A 213 Gr. T12; A 217 Gr. WC6; A 234 Gr. WP11; A335 Gr. P11, P12; A 336 Gr. F11, F12; A 426 Gr. CP12						
AGRÉMENTS	CE						
POSITIONS DE SOUDAGE	 PA  PB  PC						
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)	C	Si	Mn	P	S	Cr	Mo
	0.05	0.3	1.2	0.015	0.015	1.1	0.5
PROPRIÉTÉS MÉCANIQUES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
	690°C±15°C 2h	485	650	25	RT		HRc
ETUVAGE	Not required						
GAS ACC. EN ISO 14175	M21						



CEWELD AA B CrMo1

AA B CRM01 1,2MM

Packaging	KG/unit	EanCode
K-300	16	8720663405340