



CEWELD L-Ag5P

TYPE	Copper Phosphorus Silver Brazing Alloy.	
APPLICATIONS	Particularly recommended for sanitary and refrigerating equipment. Suitable for working temperatures up to 200 °C	
PROPRIÉTÉS	Excellent flowing alloy with high purity offering strong brazing joints. Do not use in a sulphurous environment. Flux/Paste: CEWELD Super-Flux	
CLASSIFICATION	AWS EN ISO F-nr	A 5.8: BCuP-3 17672: CuP 281 103

CONVIENT POUR Copper to Copper (without flux). Brass, Copper and Copper-Tin Alloys (with flux).

AGRÉMENTS

POSITIONS DE SOUDAGE



ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)

Cu	Ag	P
Rem.	5	6

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A5 (%)	Hardness
As Welded		250		HRc

ETUVAGE Not required

MELTING RANGE 645 - 815°C

GAS ACC. EN ISO 14175



CEWELD L-Ag5P

L-AG5P 1,5MM

Packaging	KG/unit	EanCode
D-300	10,11	8720663421487