



CEWELD AlMg 3 Tig

TYPE	TIG filler metal for welding Aluminium Magnesium alloys.				
TOEPASSINGEN	Suitable for base metals with maximum 3% Mg. These alloys are suitable for a big range of applications in the construction sector, in general, and in the structural industry. Widely used in ship and vessel building.				
EIGENSCHAPPEN	This alloy offers excelent weldability when properly cleaned prior to welding. Heavy parts and thicker plates should be preheated (150°C), prior to welding The alloy shows good corrosion-resistance and an excellent colour-uniformity after anodizing. CEWELD® AlMg3 Tig offers also good resistance against seawater.				
CLASSIFICATIE	AWS EN ISO F-nr	A 5.10: ER5754 18273: S Al 5754 (AlMg3) 22			
GESCHIKT VOOR	Aluminium alloys: AlMg Mn, AlMg 3Mn, AlMg1, AlMg2, AlMg2,7Mn, AlMg3, AlMg3,5, AlMgSi0,5, AlMgSi0,8, G-AlMg3Si, 3.3315, 3.3535, 3.3206, 3.3541, EN AW 5005A, EN AW 5754, EN AW 6060, EN AC 51100, EN AW 5454, EN AW 5251				
GOEDKEURINGEN	CE				
LASPOSITIES					
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Al Rem.		Mg 3.2		
MECHANISCHE WAARDEN	Heat Treatment As Welded	R _{P0,2} (MPa) 80	R _m (MPa) 190	A5 (%) 20	Hardness HRc
HERDROGEN	Not required				
GAS ACC. EN ISO 14175	I1, I3				



CEWELD ALMg 3 Tig

ALMG 3 TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407313
ALMG 3 TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407320
	Tube	5	8720663407337
ALMG 3 TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407344
ALMG 3 TIG 3,2 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407351
ALMG 3 TIG 4,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407368
ALMG 3 TIG 5,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407375